

Amendments to the Specification:

Please replace the paragraph beginning at page 6, line 18 as with the following amended paragraph:

Furthermore, the e) urethane reaction catalyst, a small amount of which is added during the urethane reaction, is preferably selected from the group consisting of copper naphthenate, cobalt naphthenate, zinc naphthate, n-butyltinlaurate, trisethylamine, 2-methyltriethylenediamide, and a mixture thereof, and is preferably used in an amount of 0.01 to 1 weight% of the photopolymerizable urethane acrylate oligomer composition.